

## ADLER Acryl-Spritzlack Q10 M



Water-based opaque pigmented topcoat for wooden windows and front doors for industrial and professional use

It has been matched as a system with a 3-coat structure with Aquawood TIG High Res Weiß and Aquawood Intermedio or ADLER Acryl-Spritzfüller

	PRODUCT DESCRIPTION		
General	Water-based opaque pigmented topcoat. Excellent weathering resistance, excellent permanent flexibility. The product is characterized by a high level of block resistance, very good impact strength, quick resistance to water, short drying times, improved mechanical and chemical resistance, natural appearance and good feel of the surface. Good firmness on vertical surfaces combined with optimal flow. Particularly low number of micro-bubbles with airless spray application as a result of highly active de-foaming and deaerating agents.		
Special properties and standards	<ul> <li>Proof of suitability according to DIN EN 927-2 outdoor weathering</li> </ul>		
	ÖNORM S 1555 or DIN 53160 Perspiration and saliva-proof properties		
1007	<ul> <li>ÖNORM EN 71-3 Safety of toys; migration of certain elements (free of heavy metals)</li> </ul>		
44000	• Meets the criteria of <b>baubook "Ecological invitation to tender"</b>		
	• French ordinance DEVL1104875A regarding the marking of construction coating products for their emission of volatile pollutants: A+		
Application areas	• Dimensionally stable timber components for exterior such as wooden windows, front doors or garage gates in the usage class 2 and 3 without soil contact.		
	• For humid areas (e.g. indoor pools) only with a special coating system.		
	<ul> <li>For non-dimensionally stable timber components we recommend Pullex Color 50530 or Pullex Aqua-Color 53331.</li> </ul>		
	• Please observe the relative technical data sheets of the products.		

01-18 (supersedes 10-16) ZKL 5008

p.t.o.

ADLER-Werk Lackfabrik, A-6130 Schwaz Tel: 0043/5242/6922-301, Fax: 0043/5242/6922-309, email: technical-support@adler-lacke.com

Our instructions for use are based on knowledge available currently and shall guide the buyer/user to the best of one's knowledge, but, however, must be clarified for the areas of application and processing conditions on a case-to-case basis. The buyer/user takes responsibility for the suitability and use of the delivered product. It is therefore recommended to produce a sample specimen for testing the suitability of the product. Our general terms and conditions of sale are otherwise applicable. All previous data sheets are rendered invalid with the issue of this one. Rights reserved for the modification of the container sizes, colour shades and degrees of gloss available.

## PROCESSING

## Instructions for use



- Please stir the product before use. However, prevent entry of air while stirring.
- The temperature of the product and object, and the room temperature must be at least + 15 C.
- The optimal conditions for use are between 15 25 °C with a relative atmospheric humidity between 40 80 %.
- Too high dry film thicknesses beyond around 120 µm reduce the diffusion capacity and should thus be avoided.
- Sealants must be compatible with the coat and may only be applied once the paint has dried through. Weather strips containing plasticizers tend to adhere in combination with paints. Please only use those types that have been tested.
- When changing from ADLER Acryl-Spritzlack Q10 M to other water-based paint systems, care must be taken to adequately clean the pipes and spray equipment, preferably with warm water.
- Please follow our "Working guideline for coating dimensionally stable and limited dimensionally stable construction elements" along with all standards and guidelines for window construction.

Application method	Airless	Airless air- supported (Airmix, Aircoat, etc.)	Cup gun	
Spraying nozzle (ø mm)	0.28 or 0.33	0.28 or 0.33	1.8 – 2.0	
Spraying nozzle (ø inch)	0.011 or 0.013	0.011 or 0.013	-	
Spraying angel (degrees)	20 – 40	20 – 40	-	
Spraying pressure (bar)	80 – 100	80 – 100	3 – 4	
Atomized air (bar)	-	0,5 – 1,5	-	
Spraying distance (cm)	approx. 25			
Dilution (thinning)	water			
Thinner amount added in %	0 – 5	0 – 5	10	
Application quantity (g/m <sup>2</sup> )	150 – 300 depending on the intermediate coat			
Yield per application (g/m) <sup>2)1)</sup>	600 - 300			
Yield per application (g/rm) <sup>1)</sup>	300 – 360 or 150 – 180			
Wet film (µm)	150 – 300 depending on the intermediate coat			
<sup>1)</sup> Yield including	<sup>1)</sup> Yield including addition of thinner and loss while spraying			

## 10 %

0-5%

**Application technique** 

The shape, the properties and moisture of the substrate affect the consumption/yield. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times	Dust-dry (ISO 1517) after approx. 1 hour			
(at 23 °C and 50 % rel. humidity)	Tack-free	after approx. 3 hours		
12 <sup>h</sup>	Stackable with PE fine foam	after approx. 5 hours		
	spacers			
	at room temperature:			
	Stackable with PE fine foam	Stackable with PE fine foam after approx. 130 min.		
	spacers after forced drying:			
	20 min flash-off zone			
	90 min drying phase (35 – 40°C)			
	20 min. cooling phase			
	Recoatable	after approx. 12 hours		
	The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.			
	Avoid direct sunlight (very quick drying	Avoid direct sunlight (very quick drying).		
Cleaning the working				
equipment	With water immediately after use.	With water immediately after use.		
	To remove dried paint residues we recommend using ADLER Aqu Cleaner 80080 or ADLER Abbeizer Rote Krähe 95125.			
	SUBSTRATE			
Type of substrate	Wood in accordance with the guideli	Wood in accordance with the guidelines for window construction.		
Substrate property (or condition)	from separating substances such as	The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.		
	Dimensionally stable components: 13 % +/- 2 %			
Wood moisture	Dimensionally stable components. T	3 % +/- 2 %		
Wood moisture	COATING SYSTEM	3 % +/- 2 %		
Wood moisture Primer coat	· ·			
	COATING SYSTEM	43700101		
	COATING SYSTEM 1 x Aquawood TIG HighRes Weiß 5	43700101 I data sheets of the products. d: flow coating		
Primer coat	COATING SYSTEM 1 x Aquawood TIG HighRes Weiß 5 Please observe the relative technica Low resin softwood and hardwoo 1 x Aquawood Intermedio 53663 by	43700101 I data sheets of the products. d: flow coating dwood with staining		

Intermediate sanding	Grit size 220 – 280 Remove sanding dust.	
Topcoat	1 x ADLER Acryl-Spritzlack Q10 M 43260 undiluted	
Final coat	For front doors we recommend an additionally coat with the colourless topcoat Aquawood Protect 53215.	
	Please observe the relative technical data sheets of the products.	
	MAINTENANCE AND RENOVATION	
Maintenance and renovation	The durability depends on several factors: these include particularly the type of weathering, constructional protection, mechanical stress and the choice of colour applied. To obtain long durability, preservation work is necessary in time. Therefore, we recommend annual maintenance.	
	<b>Windows</b> : Cleaning with ADLER Top-Cleaner 51696 is sufficient (for severe dirt). Maintenance with ADLER Top-Finish should not be carried out due to the risk of streaking.	
	<b>Front doors</b> : Cleaning with ADLER Top-Cleaner 51696. Preservation using ADLER Door-Finish 51700 in the ADLER Haustürenpflegeset (front door preservative kit) 51709.	
	Please observe the relative technical data sheets of the products.	
	Please follow our "Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - Maintenance and renovation".	
	ORDERING INFORMATION	
Size of trading unit	5 kg; 25 kg; 120 kg poly drum	
Color shades/degree of gloss	RAL 901043249RAL 901643248RAL 900143250RAL 703543252RAL 600543253RAL 600943254RAL 101343251	
	Other colour shades can be obtained using the ADLER colour mixing system ADLERMix.	
	Base paints: Base W10 43261 Base W30 43260	
	Glossy surfaces can be realized with ADLER Acryl-Spritzlack Q10 G.	
	Base paints: 43271 and 43270	
	Please observe the relative technical data sheets of the products.	
Supplementary products	Aquawood TIG HighRes Weiß 543700101 Aquawood Intermedio 53663 Aquawood Protect 53215 ADLER Acryl-Spritzlack Q10 G 43271, 43270 ADLER Acryl-Spritzfüller 41002 ADLER Aqua-Cleaner 80080	

ADLER Top-Cle ADLER Door-Fi ADLER Haustü	ADLER Abbeizer Rote Krähe 95125 ADLER Top-Cleaner 51696 ADLER Door-Finish 51700 ADLER Haustürenpflegeset 51709 Pullex Color 50530		
FURTHER D	FURTHER DETAILS		
At least 1 year i	At least 1 year in the original sealed containers.		
	Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).		
VOC content	EU threshold for ADLER Acryl-Spritzlack Q10 M (cat A/d): 130 g/l (2010). ADLER Acryl-Spritzlack Q10 M contains maximum 40 gm./l VOC (Volatile Organic Compounds).		
Further information on the subject of safety during transport, stora and handling as well as disposal can be found in the relevant sa data sheet. The current version can be accessed on the Interne www.adler-lacke.com.			
The product is a	The product is only suitable for industrial and professional use.		
Inhaling paint aerosols whilst spraying must generally be avoided. This is ensured by correctly using a respiratory mask (combination filter A2/P2 – EN 141/EN 143).			
	ADLER Top-Cla ADLER Door-Fi ADLER Haustü Pullex Color 50 <b>FURTHER D</b> At least 1 year i Make sure the frost and high te VOC content Further informa and handling as data sheet. The www.adler-lac The product is o Inhaling paint a This is ensured		