

## ADLER Aqua-Rapid CFB

**30451 ff**

Water-based clear multi-coat finish for **furniture and interior finishing for industrial and professional use**

### PRODUCT DESCRIPTION

#### General


Water-based clear varnish for wood surfaces, which can be optionally used as a one-component or, after adding a crosslinking agent, as a two-component system. Very good chemical and mechanical resistance; also as one-component varnish cream and grease resistant (CFB); good light-fastness; excellent transparency, high build and grain accentuation; excellent anti-sagging qualities on vertical surfaces. The product contains a special filter with very high sun protection against early yellowing or fading. Varnish-on-varnish application possible.

#### Special Properties Testing Standards

- **ÖNORM A 1605-12** (Furniture surfaces)  
Resistance to chemical reactions:  
For 1-comp. processing: 1-B  
For 2-comp. processing: 1-B1  
Response to abrasion: 2-D ( $\geq 50$  U)  
Response to scratches:  
For 1-comp. processing: 4-E ( $\geq 0,5$  N)  
For 2-comp. processing: 4-D ( $\geq 1,0$  N)
- **DIN 68861** (furniture surfaces)  
Part 1: Response to chemical stress: 1 B  
Part 2: Response to abrasion: 2 D (above 50 to 150 U)  
Part 4: Response to scratches:  
For 1-comp. processing: 4 E ( $> 0.5$  to  $\leq 1.0$  N))  
For 2-comp. processing: 4 D ( $> 1.0$  to  $\leq 1.5$  N)
- **ÖNORM A 3800-1** (Fire behaviour) in conjunction with a flame-retardant substrate:  
flame-retardant (formerly B1 in accordance with B 3800-1), Q1, Tr 1
- **DIN 4102-B1** (Highly non-combustible) in conjunction with flame-retardant laminated plywood – even veneered
- **EN 13501-1** (Fire behaviour) in conjunction with flame-retardant laminated plywood – even veneered: B-s2,d0
- **NF P 92-501** (fire behaviour **in accordance to the French construction product regulation in conjunction with a flame retardant surface: M1**)
- Highly non-combustible coating material for sea-going vessels (in accordance with **SOLAS 74/88 Chapter II-2**)



General building inspection test certificate  
P-BWU03-I-16.5.235, MPA Stuttgart




EC type test certificate 116.306  
US Coast Guard approval certificate  
164.112/EC0736/116.306

- **ÖNORM S 1555 resp. DIN 53160** Perspiration and saliva-proof properties
- **ÖNORM EN 71 Part 3** Safety of toys; Migration of certain elements (free of heavy metals)
- **French Ordinance DEVL1104875A** regarding the labelling of construction coating products with respect to their emission of volatile pollutants: A+




### Areas of application




- For high build varnishing of furniture and interior fixtures including kitchen and bathroom surfaces (excluding worktops): with two-component applications (application areas II to IV according to ÖNORM A 1610-12) for example for kitchen, bathroom, school and hotel furniture, with one-component applications (application areas III to IV according to ÖNORM A 1610-12) for example for living and bed room furniture etc.
- Ideal for varnishing chairs and other frame furniture, where excellent cream and grease resistance is required.
- Very high application reliability even with complex workpiece shapes due its viscosity characteristics.
- In combination with ADLER Aqua-Fluid 80044 attractive, distinctive grain texture on open-pore woods. **Addition of 20 – 25 % to the varnish or to varnish/crosslinking agent mixture.**
- For highly non-flammable or flame-retardant structures.

## PROCESSING

### Instructions for use



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least +15 °C.
- ADLER Aqua-Rapid CFB 30451 ff can be uses by choosing one- or two-component processing.
- ADLER Aqua-Rapid CFB 30451 ff features excellent transparency and good grain accentuation of the wood substrate. If a stronger enhancement is required, apply a wood stain or tint the varnish with up to 1 % of the specially matching ADLER Aqua-Tint light 89251, medium 89252 or dark 89253 prior to varnishing.
- To prevent discoloration or markings (these can be evident in varying degree depending on the origin of the timber), we recommend priming with ADLER PUR-Primer 25291 when varnishing **oak, larch** and **other timbers rich in extractives**. As an alternative for hardwood ADLER Aqua-Intense GL 30016 can be used as a primer.
- Please follow the respective technical data sheets of the products.
- Please follow our „**Working guidelines for water-based furniture varnish**“.
- For coating of marine interior fitting apply 2 x 120 g/m<sup>2</sup>.
- Regarding the coating of interior fittings on ships the flame-retardant surface material must not be used on pipes, pipe covers and cables.


**Blending ratio**

100 parts by weight of ADLER Aqua-Rapid CFB 30451 ff  
2 parts by weight of ADLER Aqua-Vernetzer 82210

**ADLER Aqua-Vernetzer 82210 must be carefully mixed with the painting component by stirring before use.**

**Pot Life**

3 days; mixed material must be mixed 1:1 with freshly hardened material after 3 days; it is not possible to extend the pot life beyond this.

**Application technique**

Application method	Airless	Airless pressurized (Airmix, Aircoat etc.)	Cup gun
Spray nozzle (ø mm)	0.23 – 0.33	0.23 – 0.33	1.8 – 2.0
Spraying pressure (bar)	100 - 120	60 - 90	2.5 – 3.5
Spraying air (bar)	-	1 - 2	-
Dilution (thinning)	water		
Thinner amount added in %	-	-	approx. 10
Application quantity (gm/m <sup>2</sup> )	approx. 80 - 120 per application; Total application quantity (primer and top coat) max. 450		

**Drying times**

(at 23 °C and 50 % rel. humidity )



Can be sanded or recoated

after approx. 2 h

Low temperatures and / or high levels of atmospheric humidity can increase the drying time considerably.

To improve the firmness of the subsequent coating we recommend drying overnight at room temperature. Due to this the content of residual solvents in the paint film is kept low.

The figures indicated serve as a guide and are for reference. The drying time depends on the substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

**Cleaning the tools and equipment**

Clean with water immediately after use.

Eliminate rests of dry paint with ADLER Aqua-Cleaner 80080 (diluted 1:1 with water).

**SUBSTRATE****Type of substrate**

Hardwood and softwood (solid wood, veneered, laminated wood and (coated) wood fibre materials)

**Substrate property (or condition)**

The substrate must be dry, clean, stable, free of grease and wax and free from wood dust.

<b>Preparation of the substrate</b>	<b>Hardwood:</b> sanding using grain size 150 – 180 <b>Softwood:</b> sanding using grain size 100 – 150 Use dust filter P3 while sanding or grinding.
-------------------------------------	---

### COATING SYSTEM

<b>Primer coat</b>	1 x ADLER Aqua-Rapid CFB 30451 ff
--------------------	-----------------------------------

#### Intermediate sanding



Grain size 240 – 320  
Use dust filter P2 while sanding or grinding.  
Avoid sanding straight through!

<b>Topcoat</b>	1 x ADLER Aqua-Rapid CFB 30451 ff
----------------	-----------------------------------

### CARE & REFURBISHMENT

Clean with ADLER Clean Möbelreiniger 96490 and maintain with ADLER Clean Möbelpflege 96491.

Please follow the respective technical data sheets of the products.

### NOTES ON ORDERING


<b>Trading units</b>	4 kg, 20 kg
----------------------	-------------

<b>Colour shades / Degree of gloss</b>	G10 Deep matt	30451
	G30 Matt	30453
	G50 Semi-matt	30455
	G70 Silk matt	30457
	G90 Satin glossy	30459

<b>Supplementary products</b>	ADLER Aqua-Vernetzer	82210
	ADLER Aqua-Fluid	80044
	ADLER Aqua-Tint light	89251 (spruce, ash wood etc.)
	ADLER Aqua-Tint medium	89252 (beech, cherry wood etc.)
	ADLER Aqua-Tint dark	89253 (walnut, rosewood etc.)
	ADLER Aqua-Cleaner	80080
	ADLER PUR-Primer	25291
	ADLER Aqua-Intense GL	30016
	ADLER Clean Möbelreiniger	96490
	ADLER Clean Möbelpflege	96491

### OTHER INSTRUCTIONS

#### Storage stability / Storage




At least 12 months in the original sealed containers.  
Cool, but frost-free

#### Technical Specifications

Delivery viscosity: 150 ± 10 s in accordance with DIN 53211 (4-mm-cup, 20 °C)

#### Safety-relevant information



Please follow the associated safety data sheet! The latest version can be retrieved from the Internet at [www.adler-lacke.com](http://www.adler-lacke.com).

In general, you must avoid inhaling paint aerosols. This is ensured by proper use of a breathing mask (combination filter A2/P2 – EN 141/EN 143).