

ADLER Floor-Fill



Product description	Water-thinnable binding solution for mixing with sanding dust. Very good application, quick drying and excellent sanding. Good shade matching.
Fields of application	Filling of small cracks and irregularities on sanded parquet floors.
Method of application	Filling (with a plastic or a rustproof metal putty knife)
Pre-treatment	The floor has to be dry and free of impurities (f.e. oil, fat, wax).
Application	Mix clean sanding dust from sanding (granulation 120) with ADLER Floor-Fill 42109 untill you get a mixture ready to fill. Fill the cracks and joints. For an efficient sanding it is favourable to let only less excess material on the surface. The drying time depends on the width of the joints and the conditions of drying. For very deep parts a re-sanding could be necessary. Sanding with granulation 120.
Primer	1 x ADLER Floor-Start 42110 (see technical data sheet)
Topcoat	2 x ADLER Floor-Classic 42120 (see technical data sheet) or 2 x ADLER Floor-Finish 42140 (see technical data sheet)
Thinner	The delivered drum size is ready to use.
Application and object temperatures	Not below + 10 °C
Drying time (Room temperature 20 °C)	Depending on application quantity between 30 and 90 minutes until sanding.
Work equipment	Clean with water immediately after use.
Yield value (per application)	Ca. 25 m²/l – depending on subsoil
Drum size	11
Storage life	3 years in sealed drums
Safety Information	Please observe our Safety Data Sheets!

01-10 (replaces 07-09)

ADLER-Werk Lackfabrik, A-6130 Schwaz Fon: 0043/5242/6922-190, Fax: 0043/5242/6922-309, Mail: <u>info@adler-lacke.com</u>

Our instructions are based on the current state of knowledge and should inform the buyer/user to the best of our knowledge. They are, however, not binding and are to be suited to the field of application and the working conditions. The buyer/user decides on his own responsibility about the suitability and employment of the delivered product. Otherwise our General Terms of Sale apply. With this issue, all previous information sheets are no longer applicable.