



CHARACTERISTICS

- Ready-to-use, light finishing paste
- Can be applied in one single movement
- Does not sag or shrink
- Does not crack
- Paintable after a few minutes, ideally after ± 2 hours
- Can be abraded
- Phthalate free

APPLICATIONS

- For the filling of cracks, joints and gaps of max. 50 mm deep and 50 mm wide.
- Has an extremely strong adhesion on porous materials such as stone, concrete, brickwork, plaster, etc.

TECHNICAL CHARACTERISTICS	
Type of sealant	Special acryl polymers
Consistency	Thixotropic paste
Density	0,45 g/ml
Open time	10 - 15 min.
Can be abraded	After 1 day
Can be painted	After a few minutes (ideal after ± 2 hours)
Shrinkage	Nil
Processing temperature	+5°C - +35°C
Shelf life, in the original packing in dry conditions between +5°C - +25°C	12 months
Temperature resistance	-20°C - +80°C

PACKING AND COLOURS
25 cartridges of 310 ml/box - 48 boxes/pallet
6 buckets of 1 l/box - 64 boxes/pallet
Bucket of 5 l - 60 buckets/pallet
Bucket of 10 l - 27 buckets/pallet
80 tube packaging of 75 ml/box - 40 boxes/pallet (3200 pieces) On request and with a MOQ of 1000 pieces
119 foil packaging of 80 ml with applicator/box - 30 boxes/pallet (3570 pieces) On request and with a MOQ of approximately 2500 pieces
119 foil packaging of 100 ml with applicator/box - 30 boxes/pallet (3570 pieces) On request and with a MOQ of approximately 2000 pieces
White

METHOD OF USE

Preparation

- Apply the product on a clean and dry surface.
- Bucket: Stir before use. When too dry, add one coffee spoon of water for each 250 ml **Paracryl Parafill** and stir until a smooth paste is obtained.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

Application

- Apply the product with a spatula and smooth afterwards.
- Layers of 4 to 25 mm give the best results.
- Max. 50 mm deep and 50 mm wide.
- Larger joints have to be filled in several steps with 1 day in between.
- Has to be painted twice when used outdoors.

Tooling

Finish with a wet spatula.

Cleaning

Tools: With water before it is dry.

Repairing

With the same product.

SAFETY

Safety data sheet available online at www.dl-chem.com.

LIMITATIONS

- Cannot be used on synthetic, metal and permanently humid surfaces.

TECHNICAL APPROVALS



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.