

## ADLER Seidenacryl

40751 ff



<b>Product description</b>	Water-thinnable, silky-mat coloured lacquer, based on acrylate-dispersion for the exterior and the interior with excellent allround-properties. Highly weather-resistant. Also appropriate for the varnishing of toys.
<b>Fields of application</b>	<p>Finishing lacquer for wood, steel, galvanised steel, aluminium and rigid polyvinyl chloride (PVC).</p> <p>ADLER Seidenacryl can also be used as renovation coat on firmly-adhesive alkyd resin lacquer.</p> <p>Use only sealing material and masking taps suited for water-thinnable paints (e.g. Tesa 4438 blue).</p>
<b>Application</b>	By brush (acrylic brush), roller coating (short haired roller), spraying.
<b>Priming coat</b>	<p><i>Wood</i>: 1 – 2 x ADLER Acryl-Holzgrund 41001 (refer to the technical data sheet)</p> <p><i>Metal</i> : 1 – 2 x ADLER Acryl-Unigrund 41191 ff (refer to the technical data sheet)</p>
<b>Finishing coat</b>	<p>1-2x ADLER Seidenacryl 40751 ff, according to the strain (intermediate drying time 5-6 hours)</p> <p>For <b>objects exposed to heavy weathering</b> (e.g. tin roof) we recommend ADLER Ferrocryl 41150 ff.</p>
<b>Diluent</b>	Water; for spraying add approx. 5 %
<b>Drying time</b> (ambient temperature 20° C)	Ready to be ground or re-coated after 5-6 hours
<b>Working and object temperatures</b>	<p>Not below +10° C</p> <p>High atmospheric humidity and/or low temperatures retard the drying.</p>
<b>Tools</b>	Clean with water immediately after use. Dry spray tools carefully in order to avoid rusting. Eliminate dry rests of paint with ADLER Abbeizer Rote Krähe 95125 which is easily degradable.

07-10 (replace 02-10) ZKL 4111

ADLER-Werk Lackfabrik, A-6130 Schwaz  
Fon: 0043/5242/6922-190, Fax: 0043/5242/6922-309, Mail: [info@adler-lacke.com](mailto:info@adler-lacke.com)

Our instructions are based on our current level of knowledge and are intended to advise the purchaser/user to the best of our knowledge. They must however be individually adapted to the areas of application and working conditions. The purchaser/user decides on his own responsibility concerning the suitability and use of the product we supply, which is why we recommend using a sample piece of wood in order to check the suitability of the product. Our General Terms of Sale shall otherwise apply. All previous data sheets hereby become invalid with this issue. The manufacturer reserves the right to alter container sizes, colours and available degrees of lustre.

<b>Yield value</b> (per coat)	10 – 12 m <sup>2</sup> /l, according to the condition of the support			
<b>Packing size</b>	125 ml, 375 ml, 750 ml, 2,5 l			
<b>Storage</b>	Cold, but frost-free			
<b>Storage life</b>	3 years in originally closed cans			
<b>Shades</b>	White W10	40751		
	Base W20	40752		
	Base W25	40790		
	Base W30	40753		
	Basic brown	40791	Basic blue	40792
	Basic yellow	40793	Basic green	40794
	Basic red	40795		
	Rapsgelb (Rape yellow) RAL 1021		40757	
	Feuerrot (Flamme red) RAL 3000		40759	
	Verkehrsrot (Traffic red) RAL 3020		40762	
	Enzianblau (Gentian blue)RAL 5010		40764	
	Laubgrün (Leaf green) RAL 6002		40767	
	Moosgrün (Moss green) RAL 6005		40768	
	Silbergrau (Silver grey) RAL 7001		40771	
	Lichtgrau(Light grey) RAL 7035		40774	
Nussbraun (Nut brown) RAL 8011		40776		
Cremeweiß (Cream) RAL 9001		40779		
Tiefschwarz (Jet black) RAL 9005		40780		

Further shades can be obtained using the ADLER colour blending system.

**Safety information** Please refer to the safety data sheet!  
Even when processing low-emission products the usual safety measures have to be followed.